

linea
porcelain collection
(color body-digital technology)



MARBLE SYSTEMS



universe honed
image by: Nancy Van Natta Associates

universe



WIS11869
universe honed 12"x24"
in stock

taupe blend



WIS11868
taupe blend honed 12"x24"
in stock



WIS11915
taupe blend honed bullnose 3"x24"
in stock

classic tan



WIS11867
classic tan honed 12"x24"
in stock



WIS11914
classic tan honed bullnose 3"x24"
in stock

Bullnose pieces are recommended to be used in dry areas. Note special order sizes, 18"x36" & 6"x36", are rectified. More sizes or finishes may be available through special order. Please contact your sales representative for more details.



bright honed

azul hond



WIS11865
azul honed 12"x24"
in stock



WIS11912
azul honed bullnose 3"x24"
in stock

bright honed




WIS11866
bright honed 12"x24"
in stock



WIS11913
bright honed bullnose 3"x24"
in stock

technical information

Physical Properties	Test	Industry Standards	Results Colored Body	
Water Absorbtion Size Calibrated (Non Rectified)	ASTM C373	0.5% maximum	≤ 0.1%	
	ASTM C499	• Range of Thickness (Inch)	0.040	
	ASTM C499	• Average Facial Dimension	± 0.50%	≤ 0.040
	ASTM C485	• Warpage	± 75% on any edge	≤ ± 0.50%
	ASTM C485	• Warpage	± 50% on diagonal	≤ ± 0.75%
	ASTM C502	• Wedging	± 0.50%	≤ ± 0.50%
Rectified	ASTM C499	• Range of Thickness (Inch)	0.040	≤ ± 0.50%
	ASTM C499	• Average Facial Dimension	± 0.25%	≤ 0.040
	ASTM C485	• Warpage	± 0.40% on any edge	≤ 0.25%
	ASTM C485	• Warpage	± 0.40% on diagonal	≤ 0.40%
	ASTM C502	• Wedging	± 0.25%	≤ 0.40%
Bond Strength	ASTM C482	50 Psi or Greater	> 200 psi	≤ 0.25%
Deep Abrasion	ASTM C1243	< 175 Mm³	< 150 mm³	> 200 psi
Hardness (Mohs Scale)		No Requirement	≥ 7	< 150 mm³
Frost Resistance (Freeze/Thaw)	ASTM C1026	No Sample Must Show Alterations To Surface	No Cracking or Spalling Occurred	≥ 7
Chemical Resistance	ASTM C650	No Requirement	Class A	No Cracking or Spalling Occurred
Breaking Strength	ASTM C648	250 Lbf Or Greater	≥ 350 lbf	Class A
Coefficient of Friction (Static)	ASTM C1028	No Requirement	Per collection	≥ 350 lbf



V1 = UNIFORM APPEARANCE:
Differences among pieces from the
same production run are minimal.

Bullnose pieces are recommended to be used in dry areas. Note special order sizes, 18"x36" & 6"x36" are rectified. More sizes or finishes may be available through special order. Please contact your sales representative for more details.

MARBLE SYSTEMS

www.marblesystems.com

COPYRIGHT © 2023 MARBLE SYSTEMS, INC.



[marblesystemsinc](#)



[marblesystems1](#)



[marblesystems1](#)



[marblesystems](#)



[marblesystems](#)